



Technical Report: (9618) 127-0285
Date Received: MAY 07, 2018

MAY 15, 2018
Page 1 of 4

DUONG DUC NGUYEN
CONG TY TNHH SON HOA VIET
LONG BINH, KHANH BINH, TAN UYEN, BINH DUONG

| | | | |
|-----------------------------|---------------------------|-------------------------|---------|
| Sample Description: | SON 2K TRANG BONG – HV 03 | | |
| Vendor: | CONG TY TNHH SON HOA VIET | Sample Size: | / |
| Manufacturer: | SON HOA VIET | VPN: | / |
| Buyer: | / | SKN/SKU No.: | / |
| Agent: | / | | |
| Labeled Age Grade: | / | PO No.: | / |
| Appropriate Age Grade: | / | Ref #: | / |
| Client Specified Age Grade: | / | Country of Origin: | VIETNAM |
| Tested Age Grade: | / | Assortment No.: | / |
| UPC Code: | / | Department No.: | / |
| Phase of Production: | / | ITEM#: | / |
| Color: | / | Date of Production: | / |
| Program: | / | Model/Style#: | / |
| Previous No: | N/A | Country of Destination: | / |

TEST:

- Methods of exposure to laboratory light sources-Fluorescent UV lamps

EXECUTIVE SUMMARY:

The sample(s) MEETS the following requirement(s):

- The requirement of ISO 4892-3 Cycle 2, Methods of exposure to laboratory light sources-Fluorescent UV lamps



CONG TY TNHH SON HOA VIET
Technical Report: **(9618) 127-0285**
MAY 15, 2018
Page 2 of 4

If there is any question regarding this report, please contact the following lab personnel:

Administrative inquiries, please contact:

Primary Contact: Ryan Nguyen, Tel: 84-028-37421-604 ~ 6, Ext: 112; email: ryan.nguyen@vn.bureauveritas.com
Back-up Contact: Abby Pham, Tel: 84-028-37421-604 ~ 6, Ext: 559; email: abby.pham@vn.bureauveritas.com

Technical inquiries, please contact:

Primary Contact: Terry Nguyen, Tel: 84-028-37421-604 ~ 6, Ext: 313; email: terry.nguyen@vn.bureauveritas.com
Back-up Contact: Ron Nguyen, Tel: 84-028-37421-604 ~ 6, Ext: 313; email: ron.nguyen@vn.bureauveritas.com

BUREAU VERITAS CONSUMER PRODUCTS SERVICES (VN) LTD.

TERRY NGUYEN
AUTHORIZED REPORT APPROVER – HARDLINE, TOYS & JUVENILE PRODUCTS DIVISION



RESULT(S):

| Evaluation | Citation / Method | Criteria | Results | Rating |
|--|-----------------------|---|----------------|--------|
| Methods of exposure to laboratory light sources- Fluorescent UV lamps | ISO 4892-3 Cycle 2 | After 144 hours of exposure as below, the specimens shall have no wrinkles or gaps, no physical or structural deterioration. Grade 4 minimum. <ul style="list-style-type: none"> • 8 hours dry of UVA 340 lamp, 50°C(±3⁰C) • 0.25 hour water spray • 3.75 hours condensation, 50°C(±3⁰C) | M Grade 4-5 | PASS |

Results Key:

| | | | |
|----|----------------|----|---------------|
| M | Meets | NM | Does Not Meet |
| NA | Not Applicable | NT | Not Tested |
| C | Claimed | R | Recorded |

RATING COLOR CHANGE

- 5 negligible or no change or staining
- 4 slightly changed or stained
- 3 noticeably changed or stained
- 2 considerably changed or stained
- 1 heavily changed or heavily stained

