



**BUREAU  
VERITAS**

# TEST REPORT

CHI NHANH DNTN SX-TM KEO DAN & NHUA  
TONG HOP NGHIEP PHAT  
24/15 AP BINH PHUOC B, BINH CHUAN THUAN AN,  
BINH DUONG

**LAB NO.:** (9611) 325-0226 (REVISION)  
**DATE IN:** NOVEMBER 22, 2011  
**DATE OUT:** NOVEMBER 29, 2011  
**DATE REVISED** DECEMBER 09, 2011  
**MOD. LOG IN:** /  
**WORKING DAYS:** 05  
**ADDENDUM DATE** /  
**PAGE:** 1 OF 3

**ATTN:** /  
**C.C.:** /

## SUBMISSION INFORMATION

Sample Description: PLASTIC POT  
Submitted Quantity: 10 PCS OF PLASTIC  
Style/SKU No.: /  
Manufacturer: /  
Country of Origin: /  
Re-test (Y/N): NO  
Colour/Assortment: /  
P.O. No.: /  
Buyer: /  
Country of Destination: /  
Previous report no.: N/A

## TEST INFORMATION & EXECUTIVE SUMMARY

**Evaluation To:** For compliance with Client's requirements:  
BS EN ISO 105 B02 – Part B02: Colorfastness to artificial light: Xenon arc fading lamp test (80 hours).

**Standards Employed:** As specified in above standard.

**Conclusion:** The results of the tested samples are recorded as **DATA**.

### **NOTE:**

This report was revised on DECEMBER 09, 2011 to add sample information per vendor's request.

**Note: If there are questions or concerns regarding above report, please contact the appropriate lab person.**

**Technical questions & concerns:** (Vietnamese): Kelvin Tran, 848-37421-604 ~ 6; email: kelvin.tran@vn.bureauveritas.com  
(English): Allen Hsu, Tel: 848-37421-604 ~ 6; email: allen.hsu@vn.bureauveritas.com

**Concerns regarding billing:** Primary Contact: Christine Le, Tel: 848-37421-604 ~ 6; email: christine.le@vn.bureauveritas.com  
Back-up Contact: Cindy Phan, Tel: 848-37421-604 ~ 6; email: cindy.phan@vn.bureauveritas.com

Signed for and on behalf of  
**BUREAU VERITAS CONSUMER PRODUCTS  
SERVICES VIETNAM LTD**

**ALLEN HSU  
HARDLINES DIVISION MANAGER**

PRODUCT IMAGE(S):



Figure 1 – Overall view.

STT	TÊN NHÃN HIỆU	MÃ NHÃN HIỆU
1	2K - Xám Mờ	HV 23
2	2K - Đen Nhũ Bạc	HV 35
3	2K - Nhũ Bạc (nền trắng)	HV 31
4	2K - Trắng Bóng	HV03
5	2K - Màu Xám	HV22
6	2K - Màu Vàng	HV20
7	2K - Đỏ Tươi	HV07
8	2K - Đen Bóng	HV05
9	2K - Màu Tím	HV16
10	2K - Xám Đậm	HV21

## RESULT(S):

Evaluation	Citation / Method	Criteria	Results	Rating
Colorfastness to artificial light	BS EN ISO 105 B02	Xenon arc fading lamp test (80 hours – Data)	<p><b>Sample 1: 2K Xám Mờ (HV 23)</b> Color Change: Grade 4-5 @ 80 hours</p> <p><b>Sample 2: 2K Đen Nhũ Bạc (HV 35)</b> Color Change: Grade 4-5 @ 80 hours</p> <p><b>Sample 3: 2K Nhũ Bạc (nền trắng), (HV 31)</b> Color Change: Grade 4-5 @ 80 hours</p> <p><b>Sample 4: 2K Trắng Bóng (HV03)</b> Color Change: Grade 4-5 @ 80 hours</p> <p><b>Sample 5: 2K Màu Xám (HV 22)</b> Color Change: Grade 4-5 @ 80 hours</p> <p><b>Sample 6: 2K Xám Vàng (HV 20)</b> Color Change: Grade 4-5 @ 80 hours</p> <p><b>Sample 7: 2K Đỏ tươi (HV07)</b> Color Change: Grade 4-5 @ 80 hours</p> <p><b>Sample 8: 2K Đen Bóng (HV 05)</b> Color Change: Grade 4-5 @ 80 hours</p> <p><b>Sample 9: 2K Màu Tím (HV 16)</b> Color Change: Grade 4 @ 80 hours</p> <p><b>Sample 10: 2K Xám Đậm (HV 23)</b> Color Change: Grade 4-5 @ 80 hours</p>	DATA

**COLORFASTNESS RATING  
COLOR CHANGE**

5 NEGLIGIBLE OR NO CHANGE  
4 SLIGHTLY CHANGED  
3 NOTICEABLY CHANGED  
2 CONSIDERABLY CHANGED  
1 MUCH CHANGED

**COLORFASTNESS RATING  
COLOR STAIN  
SELF STAINING**

5 NEGLIGIBLE OR NO STAINING  
4 SLIGHTLY STAINED  
3 NOTICEABLY STAINED  
2 CONSIDERABLY STAINED  
1 HEAVILY STAINED

\*\*\*\*\*