



Technical Report: (9618) 127-0273
Date Received: MAY 07, 2018

MAY 15, 2018
Page 1 of 4

DUONG DUC NGUYEN
CONG TY TNHH SON HOA VIET
LONG BINH, KHANH BINH, TAN UYEN, BINH DUONG

Sample Description:	SON THONG MING TRANG MO - STM 201 (3002P)		
Vendor:	CONG TY TNHH SON HOA VIET	Sample Size:	/
Manufacturer:	SON HOA VIET	VPN:	/
Buyer:	/	SKN/SKU No.:	/
Agent:	/		
Labeled Age Grade:	/	PO No.:	/
Appropriate Age Grade:	/	Ref #:	/
Client Specified Age Grade:	/	Country of Origin:	VIETNAM
Tested Age Grade:	/	Assortment No.:	/
UPC Code:	/	Department No.:	/
Phase of Production:	/	ITEM#:	/
Color:	/	Date of Production:	/
Program:	/	Model/Style#:	/
Previous No:	N/A	Country of Destination:	/

TEST:

- Methods of exposure to laboratory light sources-Fluorescent UV lamps

EXECUTIVE SUMMARY:

The sample(s) MEETS the following requirement(s):

- The requirement of ISO 4892-3 Cycle 2, Methods of exposure to laboratory light sources-Fluorescent UV lamps



CONG TY TNHH SON HOA VIET
Technical Report: **(9618) 127-0273**
MAY 15, 2018
Page 2 of 4

If there is any question regarding this report, please contact the following lab personnel:

Administrative inquiries, please contact:

Primary Contact: Ryan Nguyen, Tel: 84-028-37421-604 ~ 6, Ext: 112; email: ryan.nguyen@vn.bureauveritas.com
Back-up Contact: Abby Pham, Tel: 84-028-37421-604 ~ 6, Ext: 559; email: abby.pham@vn.bureauveritas.com

Technical inquiries, please contact:

Primary Contact: Terry Nguyen, Tel: 84-028-37421-604 ~ 6, Ext: 313; email: terry.nguyen@vn.bureauveritas.com
Back-up Contact: Ron Nguyen, Tel: 84-028-37421-604 ~ 6, Ext: 313; email: ron.nguyen@vn.bureauveritas.com

BUREAU VERITAS CONSUMER PRODUCTS SERVICES (VN) LTD.

TERRY NGUYEN
AUTHORIZED REPORT APPROVER – HARDLINE, TOYS & JUVENILE PRODUCTS DIVISION



RESULT(S):

Evaluation	Citation / Method	Criteria	Results	Rating
Methods of exposure to laboratory light sources- Fluorescent UV lamps	ISO 4892-3 Cycle 2	After 144 hours of exposure as below, the specimens shall have no wrinkles or gaps, no physical or structural deterioration. Grade 4 minimum <ul style="list-style-type: none"> • 8 hours dry of UVA 340 lamp, 50°C(±3⁰C) • 0.25 hour water spray • 3.75 hours condensation, 50°C(±3⁰C) 	M Grade 4-5	PASS

Results Key:

M	Meets	NM	Does Not Meet
NA	Not Applicable	NT	Not Tested
C	Claimed	R	Recorded

RATING COLOR CHANGE

- 5 negligible or no change or staining
- 4 slightly changed or stained
- 3 noticeably changed or stained
- 2 considerably changed or stained
- 1 heavily changed or heavily stained

